



FASTFIX WET SEAL

ONE COAT INSTANT
WATERPROOFING

CAN BE USED IN THE WET

NO PRIMER NEEDED

FIBRE REINFORCED

ONE COAT APPLICATION

FASTFIX WET SEAL *with fibres* – Data Sheet

PERFORMANCE ADVANTAGES

- > Ready to use straight away
- > Works instantly
- > Particularly suitable for general maintenance work
- > Contains added fibres that interlace to cover up small gaps or cracks
- > Rainfall immediately after application has no adverse effect
- > Solvent based



USES

Ready for use on flat, pitched roofs, weathered asphalt and bituminous surfaces, gutters, concrete, brickwork, fibreglass, felt and metal (galvanised and ferrous).

For other surfaces see Preparation and Application.

- > Can be brush or squeegee applied.

Not for use on Walkways, Balconies, timber surfaces, new and aged PVC, plasticised PVC (Plastisol) or internal use.

COLOUR RANGE

- > Grey only.

PACK SIZE

- > 1 kg, 2.5 kg, 5 kg containers.

SPREADING RATE

- > *Wet Seal Coat*: between 1 kg – 2 kg per square metre depending on substrate.
- > *Standard Coat*: approximately 0.5 kg per square metre depending on substrate.

DRYING TIME

- > Up to 6-7 days depending on temperature, thickness of coating.
- > The product may remain soft for a further period depending on climatic conditions, this is not detrimental to the waterproofing qualities of the product.

Not suitable for heavy foot-traffic areas

WATER REPELLENCY

- > Rainfall immediately after application has no adverse effect.

SHELF LIFE

- > Up to 2 years if stored correctly in an unopened container.

PREPARATION AND APPLICATION

Clear all areas of moss, lichen and debris by brushing or power washing and remove surface water and any contamination such as Oil or Grease and allow to dry. Apply fungicidal wash to prevent further fungal/algal growth.

Most roofing substrates to be treated will not normally require priming.

To the dry and cleaned surface, apply a generous coat of FASTFIX Wet Seal roof coating by brush or squeegee, at the minimum specified spreading rate as stated above under the heading.

Application Temperature should be between 5°C-25°C.

SUBSTRATE TYPES

Highly porous/friable surfaces

Concrete and Asbestos Cladding, Sheeting and Guttering should be primed with a primer for porous surfaces prior to over coating with FASTFIX Wet Seal waterproof roof coating.

These Surfaces – Must be jet washed prior to applying any porous surface primer.

Metal Surfaces

- > Ferrous- New, weathered and previously painted galvanised iron and steel.
- > Non-Ferrous Metals – Aluminium sheeting & aluminium alloy box gutters and previously painted non-ferrous metals.

All these areas should be suitably prepared and primed as appropriate before application of FASTFIX Wet Seal waterproof roof coating.

Non-porous substrates

Slate, polished bricks should be power washed abraded and completely dry, free from any contamination to achieve adhesion of the FASTFIX Wet Seal waterproof roof coating.

Bitumen Surfaces

Discolouration may occur over new asphalt, tar or bitumen surfaces; therefore an extra coat may be required, for decorative purposes only. Aged bitumen can be liable to crack, therefore further advice must be taken.

Previously painted or coated substrates

IT IS GOOD PRACTICE TO INSPECT AND CARRY OUT ADHESION TESTS ON ANY EXISTING COATING OR SUBSTRATE PRIOR TO APPLICATION OF THE COATING.

Splits, Cracks, Joints and Seals

Pay particular attention to clean out any splits/cracks/joints and seals by scraping or brushing off with a stiff bristle brush before applying a suitable surface primer. Repair all faults in the surface by using a propriety filler.

Crazed areas

These should be primed with a suitable surface primer prior to the application of FASTFIX Wet Seal.

In Areas where excessive movement may occur additional reinforcement must be incorporated into the coating.

IMPORTANT

- > FASTFIX Wet Seal is not recommended for the treatment of wooden surfaces, tanking, fishponds or internal use.
- > Air conditioning vents should be sealed for a minimum of 24 hours during and after application.
- > MINIMUM FINISHED FALL: When using this product we recommend a minimum finished fall of 1:80 is achieved.

CLEANING

For cleaning equipment use White Spirit or Methylated Spirits.

PRECAUTIONS

- > Flammable keep away from sources of ignition.
- > Ensure good ventilation during application.
- > Wear gloves, goggles and suitable protective clothing.
- > In case of contact with eyes rinse immediately with plenty of water and seek medical advice.
- > Remove splashed from the skin with a recognised hand cleaner or plenty of soap and water.
- > Keep out of reach of children.
- > Do not use near fishponds.
- > Toxic to aquatic organisms. May cause long term adverse effects in the aquatic environment.
- > Do not empty into drains.

SAFETY

Good working practice should be followed and safety/walking boards should be utilised where required.

The specification and coverage rates are given in good faith and are based on our experience and knowledge but without liability.

As Evo Building Products has no direct control over the method employed by the user in applying its products, any warranty either written or implied is given in good faith and can only cover the material itself.

If in doubt regarding any of the above points, please contact our technical services department for advice.

A Material Safety Data Sheet is available on request.

It is the users responsibility to ensure that this data sheet is current prior to using the product.

